
Technical Data Sheet

Si-COAT® 570™

RTV Silicone High Voltage Insulator Coating



1 Introduction

Si-COAT 570 High Voltage Insulator Coating (HVIC) is a room temperature vulcanizing (RTV) silicone product. Unlike competitive products, it is supplied ready-to-use without the need of additional thinning or excessive mixing/shaking before use. Si-COAT 570 HVIC is based on extensive research and development work that led to the award of a patent. The basis of the Si-COAT 570 patent is the optimally-sized alumina trihydrate (ATH) particle and the optimum concentration of the ATH ingredient, discovered by the engineers and chemists at CSL Silicones Inc. The presence of ATH in the formulation of the HVIC is necessary to protect the coating from the damaging effects of tracking under high electrical activity along the surface of the coating. It is essential that the ATH particle be optimally-sized and in an optimum concentration in order to promote long-term hydrophobicity of the coating.

The downside to the presence of ATH is the potential for the filler to settle during storage and transportation. In order to alleviate the problem, competitive coatings rely on a very fine particle size ATH (below 1 micron diameter). However, this fine particle size is far from the optimum size (13 microns) patented by CSL. By virtue of other key ingredients and a unique manufacturing process, the engineers and chemists behind Si-COAT 570 have achieved a finished product in which the larger 13 micron ATH particle will not settle. Hence, excessive agitation prior to application is unnecessary, making Si-COAT 570 one of the easiest HVICs to use.

Apart from its very long life and ease-of-use qualities, Si-COAT 570 was the first to introduce the benefit of strong adhesion to the insulator surface. It is ideally suited for unprimed application to glass, porcelain and polymer (silicone and EPDM) insulators under all voltage conditions from distribution to very high voltage. Over its greater than 15 years of service history, Si-COAT 570 has distinguished itself from its competition by virtue of flawless performance without a single failure of any type. That is far more than any competitor can claim of their HVIC.

For ultimate suppression of leakage current and an untarnished service life greater than that of any other HVIC, turn to Si-COAT 570 by CSL Silicones Inc.

2 Product Description

A single component, RTV, moisture cure, high-build polysiloxane coating providing excellent long-term hydrophobicity, hydrophobicity recovery, electrical characteristics and UV tolerance leading to suppression of leakage current, reduction of pollution related flashover risk and a long service life.

3 Intended Uses

Suitable for use on both new insulators and old insulators to be refurbished. Can be used, unprimed, on a variety of insulator substrates including glass, porcelain, HTV silicone, LSR type silicone and EPDM.

Further suitable as a refresh coating over old silicone HVICs provided the old HVIC is properly cleaned and still displays strong adhesion to the insulator surface.

Can be used in a wide variety of pollution environments including, but not limited to, salt spray, salt fog, industrial (cement dust, fly ash, carbon black, acid emissions, etc.) and desert sand.

Designed for use in AC and DC systems, in substations of all voltage levels and on transmission lines under all voltage conditions ranging from low distribution voltages to very high transmission voltages.

4 Practical Information

Color	Standard color is grey. Custom colors may be available dependent on formulation requirements.
Gloss Level	Semi-gloss
Percent Solids	57% by volume 70% by weight
Typical Thickness	15.0 to 20.0 mil (381 to 508 micron) dry film thickness (DFT) <i>Equivalent to...</i> 26.0 to 35.0 mil (660 to 890 micron) wet film thickness (WFT)

Theoretical Coverage	<i>DFT</i>	<i>15.0 mils</i> (381 μ)	<i>20.0 mils</i> (508 μ)
	<i>sq. ft per US gal</i>	61.0	45.7
	<i>sq. ft per lb</i>	6.5	4.9
	<i>sq. m per liter</i>	1.5	1.1
	<i>sq. m per kg</i>	1.3	1.0
Practical Coverage	Allow appropriate loss factor and calculate as follows: Practical Coverage = Theoretical Coverage x [100% - Loss%]		
Method of Application	Airless spray, brush or dip		
Application Temperature Range	41 to 140°F (5 to 60°C) <small>[ambient]</small> 41 to 266°F (5 to 130°C) <small>[substrate]</small>		
Drying Time	<i>Skin-over Time:</i>	15 minutes <small>(at standard conditions)</small>	
	<i>Tack-free Time:</i>	30 minutes <small>(at standard conditions)</small>	
	<i>Cure Through:</i>	6 hours <small>(at standard conditions)</small>	
	<i>Full Physical Characteristics:</i>	7 days <small>(at standard conditions)</small>	

5 Regulatory Data

Flash Point	100°F (38°C)
Product Weight	9.4 lb/US gallon (1.13 kg/liter)
VOC	3.26 lb/US gallon (390.10 g/liter)

6 Physical Properties

UNCURED	
Appearance	Thick paint
Viscosity	1,350 ± 150 cP
Cure System	Neutral, moisture cure
CURED <small>At standard conditions for 7 days</small>	
Dielectric Strength	735.5 V/mil (290.5 kV/cm) <small>[ASTM D149]</small>
Volume Resistivity	2.9 x 10 ¹⁶ Ω.in (7.3 x 10 ¹⁶ Ω.cm) <small>[ASTM D257]</small>
Surface Resistivity	2.2 x 10 ¹⁵ Ω.in (5.5 x 10 ¹⁵ Ω.cm) <small>[ASTM D257]</small>
Dissipation Factor	at 100 Hz: 0.01; at 100 kHz: 0.0057 <small>[ASTM D150]</small>
Dielectric Constant	at 100 Hz: 3.93; at 100 kHz: 3.86 <small>[ASTM D150]</small>
Tracking Wheel Withstand	>1000 hrs.
Dry Arc Resistance	track: 180 sec; burn out: 450 sec
Temperature Stability	-40 to 480°F (-40 to 250°C)
Thermal Expansion Coefficient	(0.24 x 10 ⁻⁴ cm/cm.°C)

* Standard conditions are 77°F (25°C) and 50% relative humidity

Thermal Conductivity	0.170 BTU/hr.ft.°F (7.0 x 10 ⁻⁴ Cal/sec.cm.°C)
Loss Tangent at 60 Hz	5.5 x 10 ⁻³
Water Repellency Angle	120 degrees
UV Accelerated Weathering	No degradation [ASTM G53 Series, 5000 hours]

7 Surface Preparation

All surfaces to be coated should be free of dirt, dust, grease, oil, release agents, curing compounds, and other foreign matter including frost. In addition, prior to applying the coating, all surfaces must be dry. Such precaution will ensure proper adhesion of the Si-COAT 570 coating to the insulator surface.

High-pressure water washing is the suggested method for cleaning the insulator surface. The recommended pressure washing parameters are 3,000 psi @ 8 – 10 gallons per minute (210 kg/cm² @ 30 – 40 liters per minute). Insulators contaminated with cementitious material should be cleaned with a dry abrasive cleaner such as crushed corncob or walnut shells mixed with limestone.

For insulators covered in silicone or hydrocarbon grease, remove the bulk of the grease with a dry abrasive cleaner as above, or by hand wiping with a rag. Once the bulk of the grease has been removed, the surface should be wiped clean using an oil-free solvent such as acetone. Isopropyl alcohol is suggested for the final wipe and coating should commence once the insulators are dry.

If for whatever reason the Si-COAT application is delayed after cleaning of the insulator, the insulator must be re-cleaned.

8 Coating Application

Mixing	Si-COAT 570 is supplied as a one-part, ready-to-use coating. It is normal, however, during shipment or extended storage, for carrier solvent to rise to the top of the container. Upon opening of the container, mix by hand or by power agitator until an even consistency of coating is obtained.
Application	<p>All surfaces should be clean and dry prior to application. The coating should be applied in a manner that prevents runs, sags, drips, spills, etc. and that completely covers surfaces without holidays. The temperature of the surface to be coated should be between 41 and 122°F (5 and 50°C) and environmental temperature should be at least 5°F (3°C) above the dew point prior to and during application.</p> <p>All areas particularly prone to corrosion such as the caps and pins of insulator discs can also be coated to provide added protection and a uniform monolithic surface.</p> <p>The entire insulator should be coated with a minimum 15.0 mil (381 micron) to 20.0 mil (508 micron) DFT of Si-COAT 570. The maximum advisable DFT of Si-COAT 570 is 50 mil (1,270 micron).</p>
Airless Spray	<p><i>Recommended</i></p> <ul style="list-style-type: none"> - Tip sizes to range from 17 to 21 thou (432 to 533 micron) with a 6 to 10 inch (15 to 25 cm) fan at 1 ft (30 cm) distance - Pump pressure ratio of 40:1 - Total output fluid pressure at spray tip not less than 2,000 psi (141 kg/cm²) - minimum ½ in (1.3 cm) ID, maximum 50 ft (15 m) length spray line - See recommended spray apparatus in Section 9

Dip	<i>Suitable</i>	<ul style="list-style-type: none"> - Constant nitrogen purge should be used over liquid surface in container to avoid formation of skins while dipping - Rotate insulators after dipping to avoid formation of drip marks - Generally, higher DFT is achieved. Thinning may be necessary
Brush	<i>Suitable</i>	<ul style="list-style-type: none"> - Generally, 10 to 15 mil (254 to 381 micron) DFT can be achieved
Thinner	Naphtha or Odorless Mineral Spirits. It is recommended, however, that Si-COAT 570 be used at the viscosity supplied. If product is thinned, do not exceed local environmental legislation.	
Cleaner	Naphtha or Odorless Mineral Spirits.	
Work Stoppages & Restarts	<p>It is not recommended that prolonged work stoppages occur upon only partial consumption of a container of Si-COAT 570.</p> <p>If work must stop after only a portion of a container of Si-COAT 570 is consumed, seal air and moisture contact from coating by covering the surface of the coating with a sheet of polyethylene film. Reseal the container to be airtight.</p> <p>Upon reopening the container to restart work, peel back the polyethylene film. If curing of the coating has occurred, use a utility knife to cut the cured coating away from the wall of the container. Peel away the cured layer of coating to expose fresh coating underneath.</p>	
Clean-up	<p>Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with cleaner as selected from above.</p> <p>Fully cured coating is environmentally benign and suitable for landfill disposal. However, always check local environmental regulations before disposal.</p>	

9 Recommended Spray Apparatus

<i>Part Description</i>	<i>Graco Part No.</i>
2 gallon ASME 100% stainless steel pressure tank with air-powered agitator	236-156
Gun/air dual regulation kit	235-042
Fluid outlet strainer	240-418
HVLP (High Volume, Low Pressure) spray gun complete with 0.042 in. (1.067 mm) fluid nozzle	239-560
Air spray gun complete with 0.110 in. (2.794 mm) fluid nozzle	239-545
Fluid hose assembly, nylon tube, neoprene cover 25 ft. (7.6 m) length, 3/8 in. (9.5 mm) ID	205-142
Air hose assembly, BUNA-N tube, neoprene cover 25 ft. (7.6 m) length, 5/16 in. (7.9 mm) ID	210-867
Polyethylene tank liner (20 per case)	112-632
Air line desiccant dryer	106-493
Air line filter	106-149
Repair kit for HVLP gun needle/nozzle	239-601
Repair kit for air spray gun needle/nozzle	239-595
Graco gun repair kits for spray guns	237-398
Tips for airless spray gun	286-xxx

[xxx refers to the last three part numbers of Graco tips]

10 Product Characteristics

Level of sheen and surface finish is dependent on application method. Avoid using a combination of application methods whenever possible. Best results in terms of gloss and appearance will always be obtained with airless spray.

If overcoating after weathering or ageing, ensure the coating is fully cleaned to remove all surface contamination such as dust, grease, oil, salt crystals, traffic fumes, etc. before application of a further coat of Si-COAT 570.

This product must only be thinned using the recommended thinners. The use of alternate thinners may inhibit the curing mechanism of the coating.

Do not apply to substrate temperatures below 41°F (5°C).

When applying Si-COAT 570 in confined spaces ensure adequate ventilation and/or respiratory equipment. Consult Si-COAT 570 MSDS for further details.

Condensation occurring during or immediately following application may result in a matte finish.

Si-COAT 570 has excellent tolerance to airborne chemical exposure. When severe chemical or solvent splashing/pooling is likely to occur please contact CSL Silicones Inc. for information regarding suitability.

11 Systems Compatibility

The following primers/intermediates are suitable for use with Si-COAT 570:

CSL-944™ Primer

All Si-COAT® branded products are compatible for use as basecoats or topcoats with each other.

12 Safety Precautions

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given in this document, the Material Safety Data Sheet (MSDS) and the container(s), and should not be used without reference to the MSDS that CSL Silicones Inc. has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes may be emitted that will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult CSL Silicones Inc. for further advice.

13 Packaging

<i>Package Size</i>	<i>Product Volume</i>	<i>Product Weight</i>	<i>Shipping Weight</i>
1 US gal unit	1.0 US gal (3.8 liter)	9.5 lb (4.3 kg)	11.0 lb (5.0 kg)
2.5 US gal unit	2.5 US gal (9.5 liter)	23.6 lb (10.7 kg)	26.5 lb (12.0 kg)
5 US gal unit	5.0 US gal (18.9 liter)	47.1 lb (21.4 kg)	51.5 lb (23.4 kg)
50 US gal unit	50.0 (189.3 liter)	470.6 lb (213.9 kg)	514.8 lb (234.0 kg)

For availability of other package sizes, please contact CSL Silicones Inc.

14 Storage

Shelf Life Minimum 12 months from date of manufacture at 90°F (32°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat or ignition.

Disclaimer

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this document without first obtaining written confirmation from CSL Silicones Inc. as to the suitability of the product for the intended purpose does so at his/her own risk. Any warranty, if given, or specific Terms & Conditions of Sale are contained in CSL's Terms & Conditions of Sale, a copy of which can be obtained upon request. While CSL endeavors to ensure all advice it gives about the product (whether in this document or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless CSL specifically agrees in writing to do so, it does not accept any liability whatsoever or howsoever arising for the performance of the product, or for any consequential loss or damage arising out of the use of the product. The information contained herein is liable to modification from time-to-time in light of experience and CSL's policy of continuous product improvement.

It is the user's responsibility to check that this document is current prior to using the product.

CSL Silicones Inc.

Worldwide
CSL Silicones Inc.
144 Woodlawn Road West
Guelph, ON N1H 1B5
CANADA

Tel: +1 519.836.9044
Fax: +1 519.836.9069

www.si-coat.com